

Product data sheet

SUPERLA[®] 40

Paraffinum Perliquidum, Light Liquid Paraffin

<u>Parameter</u>	<u>Methods</u>	<u>Dimension</u>	<u>Values</u>
Saybolt Colour	ASTM D156		min. 30
Density 15°C	DIN EN ISO 3675	g/cm ³	0,830 - 0,870
Rel. Density 20/20	Ph. Eur. 2.2.5		0,810 - 0,875
Flashpoint COC	ASTM D92	°C	min. 165
Pourpoint	ASTM D97	°C	max. - 6
Kin. Viscosity 20°C	ASTM D445	mm ² /s	ca. 36
Kin. Viscosity 40°C	ASTM D445	mm ² /s	14,5 - 17,5
Kin. Viscosity 100°C	ASTM D445	mm ² /s	ca. 3,5
Dyn. Viscosity 20°C	Ph. Eur. 2.2.9	mPas	25 - 80
Typial Carbon Type	ASTM D2140		
C _A		% w/w	0
C _N		% w/w	35
C _P		% w/w	65
European Pharmacopoeia (PH.EUR.) latest version			pass
United States Pharmacopoeia (USP) / National Formulary (NF) latest version			pass
FDA 178.3620(a)			pass

This product data sheet and the information within were assembled and checked with utmost care and are to be regarded as accurate as of the date of issue. Nevertheless, PARAFLUID GmbH takes no responsibility or warrant for its timeliness, completeness, quality or correctness. This product data sheet is for information only and does not warrant any particular product properties. It is the user's obligation to check the products and use them safely as well as to comply with all applicable laws and regulations. PARAFLUID GmbH shall not be responsible for any damage or injury in particular resulting from use, other than the stated use of the material, from any failure to abide to recommendations, or from any dangers inherent in the nature of the material. It is recommended to contact the manufacturer for further information, especially if it is intended to use the product for applications other than the stated. In addition, the most recent version of our Business Conditions will apply.



Nonfood Compounds
Program Listed (H1, HX-1, 3H)

Review: 10.2018

PARAFLUID GmbH
Schloßstraße 8c
22041 Hamburg
Germany

Phone: +49 40 63704 00
Fax: +49 40 63704 100
Mail: info@parafluid.eu
Website: www.parafluid.eu

